

Cray Valley Oaklands Corporate Center 502 Thomas Jones Way Exton, PA 19341 610-363-4100 1-877-TACK RES (877-822-5737) www.crayvalley.com

# **Technical Data Sheet:**

# Wingtack<sup>®</sup> 95 Flake

## ALIPHATIC C-5 PETROLEUM HYDROCARBON RESIN

#### DESCRIPTION

Wingtack 95 is a light yellow aliphatic resin that provides an excellent balance of tack, peel strength and cohesive strength, combined with light color, low odor, and low volatility. In addition, it possesses low melt viscosity, low specific gravity, and good color stability at compounding temperatures.

#### **PRODUCT HIGHLIGHTS**

Compatible with a wide variety of less-polar elastomers, olefins, and waxes; especially low-VA EVA, SIS, natural rubber and isoprene-based rubber. Generally soluble in solvents having low to medium polarity Low color

#### **PERFORMANCE PROPERTIES**

Elastomer Compatibility EVA Compatibility PSAs

### Wingtack 95 Flake

### TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Appearance Ash Content, wt.% Color. Gardner	Light yellow flake 0.0
(solution in 50% toluene)	1.7
FTIR Ratio, Olefinic	0.23
Mn, g/mol.	1,100
Mw, g/mol.	1,700
Softening Point, °C	98
Specific Gravity @ 25 °C	0.94
Tg (midpoint), °C	55
Tg (onset), °C	49
Heat Stability (10g for 5hrs. at 177 °C)	
Aged Gardner Color	8
Skinning	0%
Weight Loss	2.3%

Storage : all resins with a low softening point present a risk of solidifying, which increases in hot weather. Therefore for softening points of less or equal to 100 °C, we recommend : storage in a cool (25 °C max), ventilated area, out of the sunlight; do not stack pallets; avoid storage for prolonged period.

**Disclaimer** : These results obtained in our laboratory are given in good faith according to the method used and the samples checked. The values cannot be used to set specifications. They are indicated without Cray Valley's guarantee or liability. All given formulations are starting formulations and they are indicated without Cray Valley's guarantee or liability. They are based on our present technical knowledge and experience. They do not relieve processors of the responsibility of carrying out their own tests and experiments, because many factors that could influence the result may arise during processing and application; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose. Any proprietary should be respected.

Shelf life : Wingtack resins are inert and stable. Their shelf life mainly depends on the storage conditions and end use. Their average shelf life is about 2 years. This average shelf life is given without Cray Valley's guarantee because Cray Valley does not control end uses and the storage conditions at customers.