



Head office : 18F, No.95,Dun Hua South Road,, Sec. 2, Taipei,
 Taiwan 105, R.O.C.

Tel : 886-2-3701 6000 Fax : 886-2-3701 6868

Kaohsiung Plant : 2 Hsing Kung Road, Ta-She, Kaohsiung,
 Taiwan 815, R.O.C.

Tel : 886-7-351 3811-9 Fax : 886-7-351 8050

May 2006

TAIPOL TPE 3201



Polymerization System	Solution Polymerization, styrene-butadiene block copolymer
Stabilizer	Non-staining
Characteristics	Medium molecular weight, high strength, easy processing and good solubility in common adhesive solvent
Use	Asphalt modification, plastics modification, adhesive and other goods

<u>Polymer Properties</u>	<u>Specification Range</u>		<u>Test Method</u>
	<u>min</u>	<u>max</u>	
Bound Styrene	(%) 28.5	31.5	K62-TPPC-09
Volatile matter	(%) —	0.5	K62-TPFP-01
Ash	(%) —	0.2	ASTM D-5667
Specific gravity	0.95 Typical		ASTM D-792
Gel	(%) —	0.1	K62-TPFP-16
Toluene Sol. Vis. 25°C	(5%,cps) 7.5	11.5	ASTM D-3616
Hardness	(Type A) 80 Typical		ASTM D-2240