



台橡股份有限公司  
**TSRC CORPORATION**  
 A MEMBER OF CEC GROUP

**Head office : 18F, No.95, Dun Hua South Road,, Sec. 2, Taipei,**  
 Taiwan 105, R.O.C.  
 Tel : 886-2-3701 6000 Fax : 886-2-3701 6868  
**Kaohsiung Plant : 2 Hsing Kung Road, Ta-She, Kaohsiung,**  
 Taiwan 815, R.O.C.  
 Tel : 886-7-351 3811-9 Fax : 886-7-351 8050

NOVEMBER 2009

# TAIPOL SBS 4265



Polymerization System	Solution Polymerization, styrene-butadiene block copolymer
Stabilizer	Non-staining
Characteristics	Good tensile strength, excellent low temperature properties.
Use	Plastics modification, shoe sole, adhesive, general rubber goods.

### Specification Range

<u>Polymer Properties</u>		<u>min</u>	<u>max</u>	<u>Test Method</u>
Bound Styrene	(%)	37	40	K62-TPPC-09
Volatile matter	(%)	—	1.0	K62-TPFP-01
Yellow Index		—	10.0	K62-TPFP-04
Ash	(%)	—	0.1	ASTM D-5667
Specific gravity		0.96 Typical		ASTM D-792
Gel	(%)	—	0.1	K62-TPFP-16
Melt flow(190°C /5 kg,	g/10min.)	11	29	ASTM D-1238
Hardness	(Type A)	90 Typical		ASTM D-2240