

May 2006

TAIPOL SBS 4230



Polymerization System	Solution Polymerization, styrene-butadiene block copolymer
Stabilizer	Non-staining
Characteristics	Good tensile strength, excellent low temperature properties.
Use	Asphalt blending, plastics modification, shoe sole, adhesive, general rubber goods.

<u>Polymer Properties</u>	<u>Specification Range</u>		<u>Test Method</u>
	<u>Min</u>	<u>max</u>	
Bound Styrene (%)	36	39	K62-TPPC-09
Volatile matter (%)	—	0.5	K62-TPFP-01
Ash (%)	—	0.1	ASTM D-5667
Specific gravity	0.96 Typical		ASTM D-792
Gel (%)	—	0.1	K62-TPFP-16
Melt flow(190 ⁰ C /5kg, g/10min.)	8	18	ASTM D-1238
Hardness (Type A)	87 Typical		ASTM D-2240