

## TAIPOL®

#### **POLYMER DATA**

### **DEC 2010**

# TAIPOL®SEBS 6154

Polymerization System Solution Polymerization.

Styrene ethylene/butylene block copolymer.

Stabilizer Nonstaining.

Characteristics Linear/medium molecular weight, superior

weather and heat resistance ,high strength and good compatibility with polyolefin plastics.

Uses Plastic modification, Asphalt modification,

Toys, Industry, Sports and other compounding

goods.

### **Specification Range**

<b>Polymer Properties</b>		<u>min</u>	<u>max</u>	<b>Test Method</b>
Bound Styrene	(%)	31.0	34.0	TPPC-13
Volatile Matter	(%)	_	0.5	TPFP-01
Yellow Index			4	TPFP-03
Ash	(%)	_	0.5	ASTM D-5667
Gel	(%)	_	0.1	TPFP-09
Specific Gravity		0.91Typical		ASTM D-792
Molecular weight		Medium		TPFP-04